

STYACRYL V 500

Polymer Emulsion

1 | Page

Version: 2.1

TDS EU/EN

Characteristics

Styacryl V 500 is a non-plasticized aqueous copolymer dispersion based on **Vinyl acetate and acrylic acid esters**. Stabilized by protective colloid and surfactant.

General Features

Styacryl V500 is raw material for the paints and coating industry. Including:

- △ Interior paints, flat to semi-gloss
- △ Primers
- △ Textured coatings

With medium pigment volume concentrations, it is universal copolymer emulsion for solvent-based interior coatings.

Physical Properties

Supply Specification	Method *	Unit	Value
Solids content (130 °C, 30min)	ISO 3251	%	50±1
Brookfield viscosity (25 °C,3/20)	ISO 2555	mPa.s	1500 ±500
pH value	ISO 976		4.0±1

Film Properties

Further Typical Properties **	Method *	Unit	Value
Particle size		µm	approx. 0.5
Minimum film forming temperature	ISO 2115	°C	7
Glass transition temperature	ISO 16805	°C	approx. 12
Appearance of the film	Soft ,Flexible, Clear and Tack free		

*According to this standard.

Usage

The usual titanium dioxide and colored pigments as well as fillers or extenders are used for the formulation of paints. To ensure adequate storage stability long-term storage trials are recommended at any rate, especially when fillers and colored pigments with a large specific surface area are chosen. In addition to the widespread used polyphosphates the salts of low molecular weight polyacrylic acids working as dispersing agents should also be used to achieve further stability.

Preservation and Storage

The dispersion contains some initial preservatives to prevent attack by microorganisms. In order that the product sufficiently protected against microbial contamination during further storage in opened drums, tanks or other storage facilities a suitable preservative should be added despite our preliminary preservation measures and the tanks and pipe work should be kept adequately clean.

Styacryl V 500 has minimum shelf life of 6 months from the dispatch date, provided the product is at temperatures between 5 °C and 35° C, avoiding frost and direct sunlight. Furthermore, it must be ensured that already opened drums and containers are always tightly closed. For bulk storage, additional conditions like the addition of preservatives or frequent stirring are technically applicable and recommended. To remove any skins or lumps that could be formed during longer storage of the dispersion due to its film forming nature a filtration or sieve process is recommendable before further processing. The technical data ascertained by our quality control laboratory at the time of product release may vary according to the storage time and storage conditions and may deviate from the original values.

Product Safety and Environmental Protection

The usual protective measures employed during the handling of aqueous polymer emulsions should be observed. Further product safety information can be obtained from our material safety data sheet that is available on request.

This information is based on our present state of knowledge and is intended to provide general notes on our products and their uses. However, we do not assume any liability whatsoever for the accuracy or completeness of the information herein. It should therefore not be construed as an expressed or implied warranty of specific properties of the products or the suitability for a particular use. Any existing industrial property rights must be observed. The quality of our products is governed by our General Conditions of Sale. In every case we urge and recommend that purchasers before using any product in full-scale production make their own test to determine to their own satisfaction whether the product is of acceptable quality and is suitable for their particular purposes under their own operating conditions