

# STYACRYL A 205

Polymer Emulsion

1 | Page

Version: 1.0

TDS EU/EN

### Characteristics

**Styacryl A205** is colloid free aqueous copolymer emulsion based on Acrylics and Methyl Methacrylic Acid esters.

### General Features

**Styacryl A205** is raw material for the paints and coatings industry, including:

- ❖ Gloss paints
- ❖ Textured coatings
- ❖ Metal corrosion protection paints
- ❖ Marble chip plasters
- ❖ Penetrating Primers

### Advantages

- High pigment volume concentrations, the emulsion offers good outdoor durability.
- Emulsion has a glossy form and crack free flexible film.
- Normal scratch, block resistance and water resistance.
- Film coatings have good resistance to aging and have a good adhesion on wet old oil and alkyd resins.

### Physical Properties

Supply Specification	Method *	Unit	Value
Solids content (130 °C , 30min)	ISO 3251	%	49±1
Brookfield viscosity (25 °C,2/50)	ISO 2555	mPa.s	500 ±200
pH value	ISO 976		7.0-9.0

### Film Properties

Further Typical Properties	Method *	Unit	Value
Particle size		µm	approx. 0.1
Minimum film forming temperature	ISO 2115	°C	5
Glass transition temperature	ISO 16805	°C	7
Appearance of the film	Medium hard ,flexible, clear and tack free		

\*According to this standard.

## Usage

**Styacryl A205** dries at temperatures higher than approx. 5 °C to form crack-free films with high elasticity, high alkali resistance and low water absorption. Because of the low MFFT of the emulsion, very small amount coalescing agents is needed to reach necessary drying of the paint. When applying pigmented gloss paints in thick coatings or on highly porous substrates it is advisable to use sufficient amounts of propylene glycol to prolong the open time. An over dosage may however have an adverse effect on the wet adhesion. The usual titanium dioxide and colored pigments as well as fillers may be used for the formulation of paints. To ensure an adequate storage stability long term storage trials are recommended at any rate, especially when fillers and colored pigments with a large specific surface area are chosen. Salts of low molecular weight polyacrylic acids work well as dispersing agents, sometimes in combination with suitable wetting agents. Depending on the nature of the pigments and extenders, the required quantity is in range between 0.1 and 0.4 % active substance of dispersing agent relative to the pigment/extender mixture. To obtain high gloss values of the dried paint film it is necessary to use a mill base. The addition of suitable associative acrylic PU thickeners imparts rheological properties to gloss paints similar to those of conventional alkyd paints. Many commercially available defoamers can be included in order to prevent excessive foaming in the paints. Trials must be carried out to determine the most suitable grades.

## Preservation and Storage

The emulsion contains some initial preservatives to prevent attack by microorganisms. In order that the product is also sufficiently protected against microbial contamination during further storage in opened drums, tanks or other storage facilities a suitable preservative should be added despite our preliminary preservation measures and the tanks and pipe work should be kept adequately clean. Styacryl A205 has minimum shelf life of 6 months from the dispatch date, provided the product is at temperatures between 5 °C and 25° C, avoiding frost and direct sunlight. Furthermore, it must be ensured that already opened drums and containers are always tightly closed. For bulk storage, additional conditions like the addition of preservatives or frequent stirring are technically applicable and recommended. To remove any skins or lumps that could have been formed during longer storage of the dispersion due to its film forming nature a filtration or sieve process is recommendable before further processing. The technical data ascertained by our quality control laboratory at the time of product release may vary according to the storage time and storage conditions and may deviate from the original values.

## Product Safety and Environmental Protection

The usual protective measures employed during the handling of aqueous polymer emulsions should be observed. Further product safety information can be obtained from our material safety data sheet which is available on request.

This information is based on our present state of knowledge and is intended to provide general notes on our products and their uses. However, we do not assume any liability whatsoever for the accuracy or completeness of the information herein. It should therefore not be constructed as an expressed or implied warranty of specific properties of the products or the suitability for a particular use. Any existing industrial property rights must be observed. The quality of our products is governed by our General Conditions of Sale. In every case we urge and recommend that purchasers before using any product in full-scale production make their own test to determine to their own satisfaction whether the product is of acceptable quality and is suitable for their particular purposes under their own operating conditions